

PRODUCT DATA SHEET

UltraClean™ UCW3700

Polystyrenic Gel, Gel, Mixed Bed Resin, Hydrogen form, Hydroxide form, Ultrapure Water Grade

PRINCIPAL APPLICATIONS

- Ultrapure Water

SYSTEMS

- Mixed bed demineralizer

REGULATORY APPROVALS

- IFANCA Halal Certified

TYPICAL PACKAGING

- 1 CF Box
- 50 L Drum (Plastic)
- 5 ft³ Drum (Fiber)

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
TOC (max.)	< 10 ppb TOC after 40 BV of rinse at 30 BV/h (*)	
Resistivity	> 18 MΩ cm after 15 BV rinse at 30 BV/h (*)	
Shipping Weight (approx.)	685 - 725 g/L (42.8 - 45.3 lb/ft³)	
Temperature Limit	60 °C (140.0 °F)	
Component Name	UltraClean Grade Gel Cation	UltraClean Grade Gel Type I Anion
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H ⁺ form	OH ⁻ form
Cation / Anion Chemical Equivalent Ratio	1	1
Total Capacity (min.)	1.8 eq/L (H ⁺ form)	1 eq/L (OH ⁻ form)
Mean Diameter	610 ± 40 μm	570 ± 50 μm
Conversion (min.)	99.9 % (H ⁺ form)	95 % (OH ⁻ form)
Moisture Retention	49 - 54 % (H ⁺ form)	60 - 70 % (OH ⁻ form)
Uniformity Coefficient	1.2	1.2
Footnote	* Influent rinse water quality : > 17.5 MΩ cm; < 2 ppb TOC	

Purolite, an Ecolab company, is a leading manufacturer of quality ion exchange, catalyst, adsorbent and specialty high-performance resins with global sales support.



We're ready to solve your process challenges.

For further information on Purolite products and services, visit www.purolite.com or contact us at the addresses below.

Americas
americas@purolite.com

Asia Pacific
asiapacific@purolite.com

EMEA
emea@purolite.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.